



September 12, 2017

Mr. Dave Hoyt
Curecrete Distribution, Inc.
1203 Spring Creek Place
Springville, UT 84663

Dear Mr. Hoyt:

On behalf of the National Floor Safety Institute, I would like to thank you for submitting your product for Phase 1 testing. The product listed below was tested per the ANSI/NFSI B101.1-2009 Test Method for Measuring Wet SCOF of Common Hard-Surface Floor Materials and the ANSI/NFSI B101.3-2012 Test Method for Measuring Wet DCOF of Common Hard-Surface Floor Materials on September 11, 2017. The average Static Coefficient of Friction (SCOF) and Dynamic Coefficient of Friction (DCOF) for the product is listed below.

Product Name(s)	AVG SCOF	Phase 1 Pass/Fail	AVG DCOF	Phase 1 Pass/Fail
Ashford Formula	0.67	Pass	0.54	Pass

The product met our minimum acceptable wet SCOF value of 0.60 and our minimum wet DCOF value of 0.42, therefore the product is eligible for Phase 2 testing. The product was tested per Phase 1 of our certification process with an NFSI Approved Tribometer and does not reflect real-world performance as evaluated in Phase 2 testing therefore the product is not NFSI Certified. Please feel free to contact us if you have any questions.

Again, thank you for submitting your product to the NFSI.

Sincerely,

A handwritten signature in blue ink, appearing to read "Russell J. Kendzior", written over a horizontal blue line.

Russell J. Kendzior
President